

# STAR PRIME™ RESINS

Grade: ABSQP6037

Molding Grade ABS Designed for Incremental Rigidity



## TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.04	D792
Melt Flow (230°C/3.8 kg)	5.0 g/10 min	D1238
<b>Mechanical</b>		
Tensile Modulus	350,000 psi	D638
Tensile Strength @ Yield	6,500 psi	D638
Flexural Modulus	350,000 psi	D790
Flexural Strength @ Yield	10,500 psi	D790
<b>Impact</b>		
Notched Izod Impact (73°F, 0.125 in)	5.0 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi-unannealed (0.125 in)	183 °F	D648
<b>Mold Shrinkage</b>		
Linear Flow	.004 - .008 in/in	D955
<b>UL Rating</b>		
	HB (1.5mm)	UL 94

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

\*STARPRIME™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

## RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	2.0 - 4.0 hrs at 180 - 200°F
Suggested Max Moisture	0.15%
Rear Temperature	370 – 425°F
Middle Temperature	400 – 450°F
Front Temperature	425 – 475°F
Nozzle Temperature	425 – 525°F
Processing (Melt) Temperature	425 – 525°F
Mold Temperature	120 – 170°F
Back Pressure	25 – 100 psi
Screw Speed	25 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet  
StarPlastics.com

Access: 12/6/17

# Navigating Custom Compounds