

STAR PRIME™ RESINS

Grade: PBTGF15

Molding Grade 15% Glass Filled PBT



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.40	D792
Mechanical		
Tensile Strength @ Yield	11,000 psi	D638
Flexural Modulus	600,000 psi	D790
Flexural Strength @ Yield	19,000 psi	D790
Impact		
Notched Izod Impact (73°F, 0.125 in)	1.5 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.250 in)	360 °F	D648
Mold Shrinkage		
Linear Flow	.004 - .006 in/in	D955

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc./SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*STARPRIME™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs, 230 - 250°F
Suggested Max Moisture	0.020%
Rear Temperature	450 – 480°F
Middle Temperature	475 – 500°F
Front Temperature	475 – 510°F
Nozzle Temperature	475 – 510°F
Processing (Melt) Temperature	485 – 525°F
Mold Temperature	120 – 190°F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 12/6/17

Navigating Custom Compounds