

# STAR PRIME™ RESINS

Grade: PC/PBTQX7026, PC/PBTQX7026UV  
Molding Grade PC/PBT, w/ UV



## TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.19	D792
Melt Flow (300°C/1.2 kg)	18.0 g/10 min	D1238
<b>Mechanical</b>		
Tensile Modulus	250,000 psi	D638
Tensile Strength @ Yield	7,100 psi	D638
Tensile Strength @ Break	6,000 psi	D638
<b>Impact</b>		
Notched Izod Impact (73°F, 0.125 in)	12.0 ft-lb/in	D256
Izod Impact, Notched Low Temp (-40°F @ 0.125 in)	10.0 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi-unannealed (0.250 in)	205 °F	D648

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc./SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

\*STARPRIME™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

## RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	3.0 - 4.0 hrs at 250 – 280 °F
Suggested Max Moisture	0.020%
Rear Temperature	450 – 480 °F
Middle Temperature	460 – 490 °F
Front Temperature	460 – 490 °F
Nozzle Temperature	475 – 500 °F
Processing (Melt) Temperature	475 – 500 °F
Mold Temperature	150 – 200 °F

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet  
StarPlastics.com

Access: 12/6/17

# Navigating Custom Compounds