

STAR PRIME™ RESINS

Grade: PC/PET7901, PC/PET7901UV
Molding Grade PC/PET, w/ UV



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.21	D792
Melt Flow (260°C/5.0 kg)	35 g/10 min	D1238
Mechanical		
Tensile Modulus	315,000 psi	D638
Tensile Strength @ Yield	8,300 psi	D638
Flexural Modulus	340,000 psi	D790
Flexural Strength @ Yield	12,500 psi	D790
Impact		
Notched Izod Impact (73°F, 0.125 in)	11.0 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.250 in)	245 °F	D648
DTUL @ 66 psi-unannealed (0.250 in)	260 °F	D648
Mold Shrinkage		
Linear Flow	.006 - .009 in/in	D955

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*STARPRIME™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	470 – 520°F
Middle Temperature	480 – 530°F
Front Temperature	495 – 540°F
Nozzle Temperature	490 – 525°F
Processing (Melt) Temperature	500 – 535°F
Mold Temperature	150 – 190 °F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 12/6/17

Navigating Custom Compounds