

# STAR PRIME™ RESINS

Grade: PCQP6005

Molding Grade PC, High Flow with Incremental Release



## TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (300°C/1.2 kg)	28.0 g/10 min	D1238
<b>Mechanical</b>		
Tensile Modulus	345,000 psi	D638
Tensile Strength @ Yield	8,700 psi	D638
Flexural Modulus	345,000 psi	D790
Flexural Strength @ Yield	13,000 psi	D790
<b>Impact</b>		
Notched Izod Impact (73°F, 0.125 in)	14.0 ft-lb/in	D256
<b>Thermal</b>		
DTUL @ 264 psi-unannealed (0.125 in)	260 °F	D648
<b>Mold Shrinkage</b>		
Linear Flow	.005 - .007 in/in	D955
<b>UL Rating</b>		
	V2(1.5mm)	UL 94

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc./SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

\*STARPRIME™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

## RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250 °F
Suggested Max Moisture	0.020%
Rear Temperature	475 – 525 °F
Middle Temperature	500 – 550 °F
Front Temperature	525 – 575 °F
Nozzle Temperature	525 – 575 °F
Processing (Melt) Temperature	525 – 575 °F
Mold Temperature	160 – 210 °F
Back Pressure	50 – 200 psi
Screw Speed	40 – 100 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet  
StarPlastics.com

Access: 11/7/18

# Navigating Custom Compounds