

ReStart™ Resins

Grade: PC7605(f1)

Molding Grade PCFR, with Elevated RTI's and (f1)
Including 50% Certified Recycled Content Materials



TYPICAL MATERIAL PROPERTIES

| Physical | Nominal Values | ASTM Test |
|---------------------------------------|---------------------|---------------|
| Specific Gravity | 1.20 | D792 |
| Melt Flow (300°C/1.2 kg) | 19.0 g/10 min | D1238 |
| Mechanical | | |
| Tensile Modulus | 350,000 psi | D638 |
| Tensile Strength @ Yield | 8,500 psi | D638 |
| Flexural Modulus | 345,000 psi | D790 |
| Flexural Strength @ Yield | 13,000 psi | D790 |
| Impact | | |
| Notched Izod Impact (73 °F, 0.125 in) | 14.0 ft-lb/in | D256 |
| Thermal | | |
| DTUL @ 264 psi-unannealed (0.125 in) | 260 °F | D648 |
| Mold Shrinkage | | |
| Linear Flow | .005 - .007 in/in | D955 |
| UL Rating | (f1) | UL746C |
| Flammability | V-2 @ 1.5mm | UL 94 |
| RTI | 125°C, 115°C, 125°C | UL 746B |

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*ReStart™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

| | Nominal Values |
|-------------------------------|------------------|
| Drying Time and Temperature | 4.0 hrs at 250°F |
| Suggested Max Moisture | 0.020% |
| Rear Temperature | 520 – 550°F |
| Middle Temperature | 530 – 570°F |
| Front Temperature | 550 – 600°F |
| Nozzle Temperature | 550 – 600°F |
| Processing (Melt) Temperature | 550 – 600°F |
| Mold Temperature | 170 – 220°F |
| Back Pressure | 50 – 100 psi |
| Screw Speed | 40 – 75 RPM |

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 2/14/19

Navigating Custom Compounds