

**STAR PLASTICS, INC**

West Virginia, United States

**MATERIAL DESIGNATION: PC75(WF)(f1), PCQP7020UV(f1) : PC7503 (f1)**

Product Description: Polycarbonate (PC), "ReStart" furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI IMP	RTI Str
BK,GY,BG	1.5	V-0	3	0	125	115	125
	2.5	V-0, 5VA	3	1	125	115	125
	3.0	V-0, 5VA	2	1	125	115	125
	3.8	V-0	-	-	125	115	125

Comparative Tracking Index (CTI): 2

Dielectric Strength (kV/mm): 24

High-Voltage Arc Tracking Rate (HVTR): 3

Dimensional Stability (%): -

Inclined Plane Tracking (IPT): --

Volume Resistivity (10<sup>x</sup>ohm-cm): 15

High Volt, Low Current Arc Resis (D495): 6

(WF) - Denotes a 2 digit number from 00 to 99 representing a customer code.

(f1) - Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C.

NOTE - Material designations may be followed by numbers and/or letters representing color and/or granulation and/or lubrication.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Last Revised: 2017-05-08

Access Date: 2018-06-27

2018 UL LLC©

**IEC AND ISO TEST METHODS**

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	1.5	V-0 (ALL)
			2.4	V-0, 5VA (ALL)
			3.0	V-0, 5VA (ALL)
			3.8	V-0, 5VA (ALL)
			6.0	V-0, 5VA (ALL)
Glow-Wire Flammability (GWF1)	IEC 60695-2-12	C	3.8	960
			6.0	960
Glow-Wire Ignition (GWI)	IEC 60695-2-13	C	3.8	800
			6.0	800
IEC Comparative Tracking Index	IEC 60112	Volts (max)	--	--
IEC Ball Pressure	IEC 60695-10-2	C	--	--
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	4.0	141
ISO Tensile Strength	ISO 527-2	MPa	--	--
ISO Flexural Strength	ISO 178	MPa	--	--
ISO Tensile Impact	ISO 8256	kJ/m <sup>2</sup>	--	--
ISO Izod Impact	ISO 180	kJ/m <sup>2</sup>	--	--
ISO Charpy Impact	ISO 179-2	kJ/m <sup>2</sup>	--	--

Star Plastics, Inc | 326 Jack Burlingame Dr, Millwood, WV 25262 USA | P: 304.273.5326 | StarPlastics.com

# Navigating Custom Compounds

