

ReStart™ Resins

Grade: PC7101(f1)

Molding Grade PCFR, 10% GF with Elevated RTI's and (f1), All colors but White

Including 50% Certified Recycled Content Materials



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (300°C/1.2 kg)	12.0 g/10 min	D1238
Mechanical		
Tensile Modulus	480,000 psi	D638
Tensile Strength @ Yield	9,400 psi	D638
Flexural Modulus	490,000 psi	D790
Flexural Strength @ Yield	14,500 psi	D790
Impact		
Notched Izod Impact (73 °F, 0.125 in)	2.50 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.125 in)	288 °F	D648
Mold Shrinkage		
Linear Flow	.003 - .005 in/in	D955
UL Rating	(f1)	UL746C
Flammability	V-0 @ 1.5mm, 5VA@2.4mm	UL 94
RTI	125°C, 115°C, 125°C	UL746B

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc./SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*ReStart™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	520 – 550 °F
Middle Temperature	530 – 570 °F
Front Temperature	550 – 600 °F
Nozzle Temperature	550 – 600 °F
Processing (Melt) Temperature	550 – 610 °F
Mold Temperature	150 – 220 °F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 2/14/19

Navigating Custom Compounds