

Orion™ RESINS

Grade: PC5FRGF10, R, UV, RUV

Molding Grade PCFR w/ 10% Glass, Release, UV, Release & UV



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.27	D792
Melt Flow (300°C/1.2 kg)	5.0 g/10 min	D1238
Mechanical		
Tensile Modulus	450,000 psi	D638
Tensile Strength @ Yield	9,500 psi	D638
Flexural Modulus	475,000 psi	D790
Flexural Strength @ Yield	14,500 psi	D790
Impact		
Notched Izod Impact (73 °F, 0.125 in)	1.5 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.125 in)	270 °F	D648
Mold Shrinkage		
Linear Flow	.003 - .005 in/in	D955
UL Rating		
	V0 (3.0 mm)	UL 94

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, Inc/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*ValuPak™ is a registered trademark of Star Plastics Inc; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs, 250°F
Suggested Max Moisture	0.020%
Rear Temperature	550 – 600 °F
Middle Temperature	575 – 625 °F
Front Temperature	600 – 650 °F
Nozzle Temperature	600 – 650 °F
Processing (Melt) Temperature	600 – 650 °F
Mold Temperature	50 – 200 °F
Back Pressure	40 – 100 psi
Screw Speed	25 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 12/6/17

Navigating Custom Compounds