

Orion™ RESINS

Grade: PC7000 (f2)

Molding Grade: FR Polycarbonate w/ 10% Glass, All Colors



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.26	D792
Melt Flow (300°C/1.2 kg)	12.0 g/10 min	D1238
Mechanical		
Tensile Modulus	480,000 psi	D638
Tensile Strength @ Yield	9,400 psi	D638
Flexural Modulus	490,000 psi	D790
Flexural Strength @ Yield	14,500 psi	D790
Impact		
Notched Izod Impact (73 °F, 0.125 in)	2.0 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.125 in)	288 °F	D648
Mold Shrinkage		
Linear Flow	.003 - .005 in/in	D955
UL Rating		
	(f2)	UL746C
Flammability	V-O @ 1.5mm, 5VA @ 2.4mm	UL 94
RTI	125°C, 115°C, 125°C	UL746B

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, LLC/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*Orion™ is a registered trademark of Star Plastics LLC; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	520 – 550 °F
Middle Temperature	530 – 570 °F
Front Temperature	550 – 600 °F
Nozzle Temperature	550 – 600 °F
Processing (Melt) Temperature	550 – 610 °F
Mold Temperature	150 – 220 °F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 11/7/18

Navigating Custom Compounds