

Orion™ RESINS

Grade: PCHC7202 (f1)

Molding Grade PCFR w/ UV and Release, All Colors

NCNB (Non-Chlorinated & Non-Brominated) FR PC



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (300°C/1.2 kg)	20.0 g/10 min	D1238
Mechanical		
Tensile Modulus	340,000 psi	D638
Tensile Strength @ Yield	9,000 psi	D638
Flexural Modulus	330,000 psi	D790
Flexural Strength @ Yield	13,000 psi	D790
Impact		
Notched Izod Impact (73 °F, 0.125)	14.0 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.250 in)	260 °F	D648
Mold Shrinkage		
Linear Flow	.004 - .006 in/in	D955
UL Rating (f1) UL746C		
Flammability	V-0 @ 3mm, V-1 @ 1.5mm	UL 94
Non-Chlorinated & Non-Brominated		UL746H

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, LLC/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*Orion™ is a registered trademark of Star Plastics LLC; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	520 – 550°F
Middle Temperature	530 – 570°F
Front Temperature	550 – 600°F
Nozzle Temperature	550 – 600°F
Processing (Melt) Temperature	550 – 600°F
Mold Temperature	170 – 220°F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 11/7/18

Navigating Custom Compounds