

Orion™ RESINS

Grade: PC/PBT7801, PC/PBT7801UV
Molding Grade PC/PBT, w/ UV



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.20	D792
Melt Flow (230°C/3.8 kg)	10 g/10 min	D1238
Mechanical		
Tensile Modulus	270,000 psi	D638
Tensile Strength @ Yield	6,500 psi	D638
Flexural Modulus	285,000 psi	D790
Flexural Strength @ Yield	10,500 psi	D790
Impact		
Notched Izod Impact (73°F, 0.125 in)	8 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.250 in)	200 °F	D648
Mold Shrinkage		
Linear Flow	.008 - .011 in/in	D955

The information provided above is based upon typical values, and are intended only as guides. Star Plastics, LLC/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*Orion™ is a registered trademark of Star Plastics LLC; SDR Plastics Inc, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	450 – 480°F
Middle Temperature	475 – 500°F
Front Temperature	475 – 510°F
Nozzle Temperature	475 – 510°F
Processing (Melt) Temperature	485 – 525°F
Mold Temperature	120 – 190°F
Back Pressure	50 – 100 psi
Screw Speed	40 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 12/6/17

Navigating Custom Compounds