

Orion™ RESINS

Grade: PCQP7056R

Molding Grade PCFR w/ Flammability Rating and Elevated RTI's



TYPICAL MATERIAL PROPERTIES

Physical	Nominal Values	ASTM Test
Specific Gravity	1.27	D792
Melt Flow (300°C/1.2 kg)	15.0 g/10 min	D1238
Mechanical		
Tensile Modulus	500,000 psi	D638
Tensile Strength @ Yield	10,000 psi	D638
Flexural Modulus	500,000 psi	D790
Flexural Strength @ Yield	15,000 psi	D790
Impact		
Notched Izod Impact (73 °F, 0.125 in)	14.0 ft-lb/in	D256
Thermal		
DTUL @ 264 psi-unannealed (0.125 in)	275 °F	D648
Mold Shrinkage		
Linear Flow	.003 - .005 in/in	D955
UL Rating		
	V-O (.620"); 5VA (0.125")	UL 94

The information provided above is based upon typical values, and are intended only as guides. Star Plastics/SDR Inc. assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

*Orion™ is a registered trademark of Star Plastics Inc; SDR Plastics, its subsidiaries or affiliates.

RECOMMENDED PROCESSING GUIDELINES

	Nominal Values
Drying Time and Temperature	4.0 hrs at 250°F
Suggested Max Moisture	0.020%
Rear Temperature	550 – 600 °F
Middle Temperature	575 – 625 °F
Front Temperature	600 – 650 °F
Nozzle Temperature	600 – 650 °F
Processing (Melt) Temperature	600 – 650 °F
Mold Temperature	50 – 200 °F
Back Pressure	40 – 100 psi
Screw Speed	25 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.

Rev0

Technical Data Sheet
StarPlastics.com

Access: 11/7/18

Navigating Custom Compounds