

GRADE: ABSQX7034

Platable Grade ABS

Typical Material Properties

Physical	Nominal Values	ASTM Test
Specific Gravity	1.06	D792
Melt Flow (230°C/3.8 kg)	5.0 g/10 min	D1238
Mechanical		
Tensile Modulus	402,000 psi	D638
Tensile Strength @ Yield	5,800 psi	D638
Flexural Modulus	410,000 psi	D790
Flexural Strength @ Yield	11,400 psi	D790
Impact		
Notched Izod Impact (73°F, 0.125 in)	3.2 ft-lb/in	D256
Thermal		
DTUL @ 264 PSI – unannealed (0.125 in)	183 °F	D648
Mold Shrinkage		
Linear Flow	.004 - .006 in/in	D955
UL Rating	HB (1.5mm)	UL 94

The information provided above is based upon typical values, and is intended only as a guide. Star Plastics, LLC assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

Orion™ is a registered trademark of Star Plastics, LLC, its subsidiaries or affiliates.

Recommended Processing Guidelines

	Nominal Values
Drying Time and Temperature	2.0 - 4.0 hrs at 180 °F – 200 °F
Suggested Max Moisture	0.15%
Rear Temperature	370 °F – 425 °F
Middle Temperature	400 °F – 450 °F
Front Temperature	425 °F – 475 °F
Nozzle Temperature	425 °F – 525 °F
Processing (Melt) Temperature	425 °F – 525 °F
Mold Temperature	120 °F – 170 °F
Back Pressure	25 – 100 psi
Screw Speed	25 – 75 RPM

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.