

Grade: ABS3030

Molding Grade ABS

Typical Material Properties

| Physical | Nominal Values | ASTM Test |
|--------------------------------------|-------------------|-----------|
| Specific Gravity | 1.05 | D792 |
| Melt Flow (230°C/3.8 kg) | 3.0 g/10 min | D1238 |
| Mechanical | | |
| Tensile Modulus | 330,000 psi | D638 |
| Tensile Strength @ Yield | 6,000 psi | D638 |
| Flexural Modulus | 350,000 psi | D790 |
| Flexural Strength @ Yield | 10,000 psi | D790 |
| Impact | | |
| Notched Izod Impact (73°F, 0.125 in) | 3.0 ft-lb/in | D256 |
| Thermal | | |
| DTUL @ 264 psi-unannealed (0.125 in) | 180°F | D648 |
| Mold Shrinkage | | |
| Linear Flow | .004 – .008 in/in | D955 |

The information provided above is based upon typical values and is intended only as a guide. Star Plastics, LLC assumes no obligation or liability for any advice furnished or for any results obtained with respect to this information. *No guarantees or warranties are expressed or implied.*

Orion® is a registered trademark of Star Plastics, LLC, its subsidiaries or affiliates.

Recommended Processing Guidelines

| | Nominal Values |
|-------------------------------|----------------------------|
| Drying Time and Temperature | 2.0 – 4.0 hrs, 180 – 200°F |
| Suggested Max Moisture | 0.15% |
| Rear Temperature | 370°F – 425 °F |
| Middle Temperature | 400°F – 450 °F |
| Front Temperature | 425°F – 475 °F |
| Nozzle Temperature | 425°F – 525 °F |
| Processing (Melt) Temperature | 425°F – 525 °F |
| Mold Temperature | 120°F – 170°F |
| Back Pressure | 25 – 100 psi |
| Screw Speed | 25 – 75 RPM |

The conditions listed above are only guidelines. You may want to adjust conditions to meet your requirements.