



Component – Plastics

E205256

Star Plastics, LLC

326 Jack Burlingame Dr, Millwood, WV 25262 USA

Material Designation: PC741, R

Product Description: Polycarbonate (PC), "STAR PRIME", Furnished as Pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI IMP	RTI Str
ALL	1.5	V-2	3	4	80	80	80
	3.0	V-2	2	4	80	80	80

Comparative Tracking Index (CTI): 3

Dielectric Strength (kV/mm): 27

Dimensional Stability (%): 0

High-Voltage Arc Tracking Rate (HVTR): 4

Inclined Plane Tracking (IPT): -

 Volume Resistivity (10⁹ohm-cm): 16

High Volt, Low Current Arc Resis (D495): 6

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliance, where the acceptability of the combination is determined by UL.

(f2) – Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure, or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL.

Access Date: 7/10/2025

2013 UL LLC©



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5 3.0	V-2 (ALL) V-2 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWI)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-